



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 9/16, 9/22, 9/50, 9/51, 9/52		A1	(11) International Publication Number: WO 99/59548																																																																																					
			(43) International Publication Date: 25 November 1999 (25.11.99)																																																																																					
(21) International Application Number: PCT/KR99/00243		(74) Agent: LEE, Won-Hee; Suite 805, Sung-ji Heights II, 642-16, Yoksam-dong, Kangnam-ku, Seoul 135-080 (KR).																																																																																						
(22) International Filing Date: 14 May 1999 (14.05.99)																																																																																								
(30) Priority Data: 1998/17740 16 May 1998 (16.05.98) KR		(81) Designated States: JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).																																																																																						
(71) Applicants (for all designated States except US): MOGAM BIOTECHNOLOGY RESEARCH INSTITUTE [KR/KR]; 341, Pojung-ri, Koosung-myon, Yongin-si, Kyonggi-do 449-910 (KR). KOREA ADVANCED INSTITUTE OF SCIENCE AND TECHNOLOGY [KR/KR]; 373-1, Kusong-dong, Yusong-ku, Taejon-si 305-338 (KR).		Published With international search report.																																																																																						
(72) Inventors; and (75) Inventors/Applicants (for US only): OH, Jong, Eun [KR/KR]; #27-804 Hanshin 3rd Apartment, Banpo 2-dong, Socho-ku, Seoul 137-767 (KR). LEE, Keon, Hyoung [KR/KR]; A-401 Green Villar, 81-12, Seongsan-dong, Mapo-ku, Seoul 121-110 (KR). PARK, Tae, Gwan [KR/KR]; #211-1501 Expo Apartment, Chunmin-dong, Yusong-ku, Taejon-si 305-390 (KR). NAM, Yoon, Sung [KR/KR]; #321-501 Zookong Apartment, Chamsil 3-dong, Songpa-ku, Seoul 138-789 (KR).																																																																																								
(54) Title: CONTROLLED DRUG DELIVERY SYSTEM USING THE CONJUGATION OF DRUG TO BIODEGRADABLE POLYESTER																																																																																								
(57) Abstract																																																																																								
<p>The present invention relates to the molecular sustained controlled release system constructed by the conjugation of molecules to be released with biodegradable polyester polymer via covalent bond and method for preparation thereof. In accordance with the present invention, the system may be formulated into microspheres, nanoparticles, or films. The molecular release rate from the above system can be regulated to be proportional to the chemical degradation rate of the biodegradable polyester polymers, resulting in near zero order kinetics profile of release without showing a burst effect. Moreover, the high loading efficiency of hydrophilic drugs can be achieved.</p>																																																																																								
<table border="1"><caption>Estimated data from the graph</caption><thead><tr><th>Time (day)</th><th>A (conjugate 50/50) (%)</th><th>B (conjugate 75/25) (%)</th><th>C (conjugate 75/25 + 50/50) (%)</th><th>D (non-conjugate) (%)</th></tr></thead><tbody><tr><td>0</td><td>0</td><td>0</td><td>0</td><td>0</td></tr><tr><td>2</td><td>10</td><td>10</td><td>10</td><td>40</td></tr><tr><td>4</td><td>20</td><td>20</td><td>20</td><td>80</td></tr><tr><td>6</td><td>30</td><td>30</td><td>30</td><td>90</td></tr><tr><td>8</td><td>40</td><td>40</td><td>40</td><td>95</td></tr><tr><td>10</td><td>50</td><td>50</td><td>50</td><td>98</td></tr><tr><td>12</td><td>60</td><td>60</td><td>60</td><td>99</td></tr><tr><td>14</td><td>70</td><td>70</td><td>70</td><td>100</td></tr><tr><td>16</td><td>80</td><td>80</td><td>80</td><td>100</td></tr><tr><td>18</td><td>85</td><td>85</td><td>85</td><td>100</td></tr><tr><td>20</td><td>90</td><td>90</td><td>90</td><td>100</td></tr><tr><td>22</td><td>92</td><td>92</td><td>92</td><td>100</td></tr><tr><td>24</td><td>94</td><td>94</td><td>94</td><td>100</td></tr><tr><td>26</td><td>96</td><td>96</td><td>96</td><td>100</td></tr><tr><td>28</td><td>98</td><td>98</td><td>98</td><td>100</td></tr><tr><td>30</td><td>100</td><td>100</td><td>100</td><td>100</td></tr></tbody></table>				Time (day)	A (conjugate 50/50) (%)	B (conjugate 75/25) (%)	C (conjugate 75/25 + 50/50) (%)	D (non-conjugate) (%)	0	0	0	0	0	2	10	10	10	40	4	20	20	20	80	6	30	30	30	90	8	40	40	40	95	10	50	50	50	98	12	60	60	60	99	14	70	70	70	100	16	80	80	80	100	18	85	85	85	100	20	90	90	90	100	22	92	92	92	100	24	94	94	94	100	26	96	96	96	100	28	98	98	98	100	30	100	100	100	100
Time (day)	A (conjugate 50/50) (%)	B (conjugate 75/25) (%)	C (conjugate 75/25 + 50/50) (%)	D (non-conjugate) (%)																																																																																				
0	0	0	0	0																																																																																				
2	10	10	10	40																																																																																				
4	20	20	20	80																																																																																				
6	30	30	30	90																																																																																				
8	40	40	40	95																																																																																				
10	50	50	50	98																																																																																				
12	60	60	60	99																																																																																				
14	70	70	70	100																																																																																				
16	80	80	80	100																																																																																				
18	85	85	85	100																																																																																				
20	90	90	90	100																																																																																				
22	92	92	92	100																																																																																				
24	94	94	94	100																																																																																				
26	96	96	96	100																																																																																				
28	98	98	98	100																																																																																				
30	100	100	100	100																																																																																				

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**Controlled drug delivery system using the conjugation
of drug to biodegradable polyester**

5 Field of the Invention

 The present invention relates to the sustained controlled release system constructed by the conjugation of drug molecules with biodegradable polyester polymer, which may be formulated into microspheres, nanoparticles or films, and method for conjugation thereof. According to the system of this invention, the drug release rate can be regulated to be proportional to the chemical degradation rate of the biodegradable polyester polymer, resulting in near zero order kinetic profile of release without showing a burst effect. Moreover, it is possible to achieve the high loading efficiency of hydrophilic drugs in the formulation into microspheres, nanoparticles, or films.

20 Description of the Prior Art

 It is difficult to maintain constant drug concentration in blood through the established injection or oral administration. Therefore, in order to maintain constant drug concentration in blood, the methods that polymer carrier is slowly degraded have been studied for the release of drug in biodegradable polymer carrier at a constant rate [Langer, R., Chem.

Eng. Commun., 6, 1-48 (1980); Langer, R. S. and Peppas, N. A., *Biomaterials*, 2, 201-214 (1981); Heller, J. CRC Crit., Rev. Ther. Drug Carrier Syst., 1(1) 39-90 (1984); Holland, S. J. Tighe, B. J. and Gould, P. L., *J. Controlled Release*, 155-180 (1986)]. Such a biodegradable polymer carrier system has an advantage that, since the polymer carrier is degraded into low molecular weight molecules, the additional elimination process of the carrier is not needed.

Many kinds of biodegradable polymers have been used as carriers, in general, aliphatic polyester polymers have been frequently used, such as poly(lactic acid), poly(glycolic acid), poly(D-lactic-co-glycolic acid), poly(L-lactic-co-glycolic acid), poly(D,L-lactic-co-glycolic acid), poly(caprolactone), poly(valerolactone), poly(hydroxybutyrate) and poly(hydrovalerate), etc. [Peppas, L. B. *International journal of pharmaceuticals*, 116, 1-9 (1995)]. In particular, poly(D-lactic-co-glycolic-acid), poly(L-lactic-co-glycolic acid), poly(D,L-lactic-co-glycolic acid) (hereinafter, generically referred to as poly(D/L-lactic-co-glycolic acid) have been widely used. It was ascribed that biodegradable polymers with various life span of degradation could be produced and drug release could be regulated for weeks or years, by controlling the molar composition ratio of monomer comprised of lactic acid and glycolic acid or controlling the

molecular weight of the polymer.

However, the formulation comprising of drugs and aliphatic polyester polymers as carriers has some difficulties in controlling the rate of drug release over a desired period due to an initial burst effect. This resulted from the fact that drug release is not dependent on the polymer erosion process but on the diffusion of drug. Particularly, this problem is serious for hydrophilic drugs such as peptides or proteins. For example, microspheres or films consisting of gentamycin sulfate and polyester polymer carrier were observed to show the initial burst effect. Also, it was reported that hydrophilic gentamycin compound had initial burst effects over 50% [Mauduit, J., Bukh, N., and Vert. M., *J. Controlled release*, **23**, 209-220 (1993); Mauduit, J., Bukh, N., and Vert. M., *J. Controlled release*, **23**, 221-230 (1993); Mauduit, J., Bukh, N., and Vert. M., *J. Controlled release*, **25**, 43-49 (1993)] and neurotensin analog over 20% [Yamakawa I., Tsushima, Y., Machida, R., and Watanable, S., *J. Pharma. Sci.*, **81**, 808-811 (1992)]. To solve such a problem, there have been efforts to develop new methods for manufacturing various microspheres, nanoparticles and films [Peppas, L. B. *International journal of pharmaceuticals*, **116**, 1-9 (1995)].

Biodegradable, biocompatible matrices for drug

delivery including microspheres, nanoparticles, and films have been widely used for an injectable depot formulation of various small molecular weight drugs, peptides, and proteins which required multiple
5 administrations. It has been known that drug release kinetic rate from the microspheres, nanoparticles, and films is determined by diffusion and/or polymer erosion process [D.D. Lewis, et al, in Biodegradable Polymers as Drug Delivery System, in M. Chasin and R. Langer
10 (Eds.), Marcel Dekker, New York (1990) pp. 1-41]. For small diameter microspheres and nanoparticles as an injectable dosage form, it has been difficult to predictably control the drug release kinetic rate over a desired period due to an initial burst effect
15 combined with the process of relatively faster diffusion of the drug than the erosion of the matrices. This problem is particularly acute for hydrophilic drugs that are believed to exist in pre-formed microporous aqueous channels within the microspheres
20 [S. Cohen, et al., *Pharm. Res.* 8 (1991) 713-720].

The most common method of preparing microspheres and nanoparticles for hydrophilic drugs is a double emulsion solvent evaporation technique which adopts a two phase emulsion system composed of polymer dissolved
25 organic phase containing primary aqueous emulsion droplets as a dispersed phase and a continuous phase of water [Y. Ogawa, et al., *Chem. Pharm. Bull.* 36 (1988)

2576-2588]. This method inevitably generates porous morphology in the microspheres and nanoparticles matrices, leading to burst and very fast release kinetics of the hydrophilic drugs through pre-existing macro- and micro-pores. For hydrophobic drugs, a single oil-in-water emulsion system has been employed to prepare drug loaded microspheres and nanoparticles. In this case, drug release kinetic rate was mainly controlled initially by diffusion through existing pores and later by polymer erosion process, resulting in a triphasic release profile. Most of previous studies for controlled release of hydrophilic drug from biodegradable polyester microspheres and nanoparticles, however, could not achieve a zero order release profile over an extended period because of complicated nature of drug release mechanism, that is, a diffusion coupled polymer erosion process [H.T. Wang, et al., *J. Controlled. Release* 17 (1991) 23-32].

On the other hand, a new drug delivery system has been developed through conjugating synthetic polymer to drug via covalent bond or modifying the biodegradable polymer. For example, the system developed by conjugating drug with polyethylene glycol(hereinafter, referred to as PEG) approved by FDA, which is hydrophilic, linear, and non-immunologic polymer, was reported to increase circulation time of the drug in

blood stream [Zhu, K. J., XiangZhou, L. and Shilin, Y.
J. Appl. Polym. Sci. 39, 1-9 (1990; Davis, F. F., Kazo,
G. M., Nucci, M. L., and Abuchwski, A., In Lee, V. H.
L.(Ed.), Peptide and Protein Drug Delivery, Dekker, New
5 York, 831-864 (1991)]. PEG has been applied to many
drugs. At least more than six classes of PEG-enzyme
complexes, including PEG-adenosine amylase, PEG-antigen,
PEG-asparaginase, and PEG-uricase, are under the
clinical trials or approved by FDA.

10

Recently, anti-cancer drugs have been chemically
conjugated to various polymers for the purpose of their
efficient passive targeting to solid tumors [R. Duncan,
et al., *Anti-cancer Drugs*, 3:175-210 (1992), .H. Maeda,
15 et al., *J. Med. Chem*, 28: 455-461 (1985), T. Minko, et
al., *J. Control Release*, 54: 223-233 (1998)]. The
"enhanced permeation and retention (EPR)" effect on the
site of tumor capillaries plays a critical role in
accumulating the polymer conjugates in the solid
20 tumors, while minimizing the glomerular excretion rate
[H. Maeda., et al., *CRC Crit. Rev. Ther. Drug Carrier*
Sys., 6: 193-210 (1989), L.W. Seymour, et al., *CRC*
Crit. Rev. Ther. Drug Carrier Sys., 9: 132-187 (1992)].
Water soluble polymer conjugates based on poly(N-(2-
25 hydroxypropyl)methacrylamide) have been extensively
studied and are now under clinical trials [V.
Omelyanenko, et al., *J Control Release*, 53: 25-37

(1998)]. Another promising approach is to conjugate doxorubicin to an amphiphilic block copolymer composed of polyethyleneglycol (PEG) and poly(α,β -aspartic acid), which leads to a polymeric micelle structure [M. Yokoyama, et al., *Bioconjugate Chem.* 3: 295-301 (1992)]. Besides the above two examples, doxorubicin has been physically adsorbed onto and/or encapsulated within nondegradable and biodegradable nanoparticles [J. Leroux, et al., *Microencapsulation: Methods and Industrial Applications*, S. Benita Ed., Marcel Dekker, New York, 535-576 (1996), P. Couvreur, et al., *J. Control. Rel.*, 17: 187 - 198 (1991)], protein nanoparticles [Y. Morimoto, et al., *Chem. Pharm. Bull.*, 29: 1433-1439 (1981)], and liposomes [A.A. Gabizon, et al., *Pharm. Res.*, 10: 703-708 (1993)., K. Yachi, et al., *Biopharm. Drug Dispos.*, 16: 653-667 (1995).]. The above doxorubicin formulations intend to achieve passive targeting of doxorubicin loaded particles to the tumor site.

20 The recent approach indicates that if the conjugation of drug with biodegradable polyester is applied to the formulation of nanoparticle, this technique will provide not only the aforementioned advantages such as high loading efficiency and zero
25 order release kinetics but also the passive targeting of the anticancer drugs to solid tumors.

Summary of the Invention

In accordance with the present invention, there is provided a novel sustained controlled release system constructed by conjugation of molecules to be released
5 with biodegradable polyester polymers.

In particular, the present invention provides a sustained controlling-release system with high loading efficiency of drug molecules.

The present invention also provides the sustained
10 controlled release system formulated into microspheres, preferably about 1 to about 300 μm in diameter, nanoparticles, preferably about 50 to about 1000 nm in diameter, or films.

In addition, this invention provides the
15 sustained controlled release system using biodegradable polyester polymer selected from the groups comprising poly(lactic acid), poly(glycolic acid), poly(D-lactic-co-glycolic acid), poly(L-lactic-co-glycolic acid), poly(D,L-lactic-co-glycolic acid), poly(caprolactone),
20 poly(valerolactone), poly(hydroxybutyrate), poly(hydrovalerate), polydioxnanone, and derivatives thereof. More preferably, the biodegradable polyester polymer is about 1,000 Da to about 100,000 Da in molecular weight.

25 This invention additionally provides the system using poly(lactic-co-glycolic acid) as a biodegradable polyester polymer with various compositions, wherein

the preferred ratio of lactic acid and glycolic acid, from 1:10 to 10: 1.

This invention provides the system employing the ester bond, amide bond, anhydride bond, urea bond, urethane bond, carbonate bond, imine bond, thioester bond, disulfide bond or carbamate bond for conjugation of molecules with biodegradable polyester polymers.

This invention also provides the system wherein the specified moieties are either directly bound to one another through covalent bond, or else indirectly bound to one another with an additional moiety such as a bridge, spacer, or linkage moieties.

Additionally, this invention provides the system wherein the molecules to be loaded are selected from the groups comprising peptides, proteins, therapeutic agents, diagnostic agent, and non-biological materials such as pesticides, herbicides, and fertilizers.

This invention also provides a process of preparing the sustained controlled release system, comprising the steps of;

- 1) activating drug molecule or polymer by mixing with coupling agents, bases, and, if needed, additives;
- 2) conjugating drug molecule with polymer by adding drug molecule to the activated polymer solution of step 1, or by adding polymer to the

- activated drug molecule solution of step 1;
3) purifying polymer-molecule conjugate of step 2.

Accordingly, an object of the present invention is
5 to provide biodegradable polyester polymer-drug
conjugates formed via covalent bond.

Another object of the present invention is to
provide biodegradable polyester polymer-drug conjugates
having an advantage that the removal process of the
10 polymer carrier is not required after drug release, as
a result of polymer degradation into low molecular
weight molecules.

Still the object of the present invention is to
provide microspheres, nanoparticles or films that are
15 easy to formulate from biodegradable polyester polymer-
drug conjugates by a single oil in water emulsion
method.

Yet another object of the present invention is to
provide microspheres, nanoparticles and films to get
20 the high loading efficiency of hydrophilic drug.

A further object of the present invention is to
provide a sustained controlled release system wherein
the initial burst of molecules is prevented and zero
order release profile is achieved by controlling the
25 molecule release rate in accordance with the chemical
degradation rate of the biodegradable polymer.

Brief Description of the Drawings

Figure 1 shows Gel Permeation chromatogram profiles of PLGA 50/50 before conjugation monitored at 230 nm (solid line) and Fmoc-Trp(Boc)-PLGA 50/50 conjugate monitored at 267 nm (dotted line).

Figure 2 shows release profiles of water soluble Fmoc-Trp(Boc)-PLGA oligomer conjugates in the medium as expressed in cumulative release percent.

Figure 3 shows pH (top) and osmolarity (bottom) change in the release medium as a function of incubation time.

Figure 4a shows the reversed phase HPLC chromatogram of released Fmoc-Trp(Boc)-PLGA conjugates from the formulation A of microspheres in Table 2 at day 7.

Figure 4b shows the reversed phase HPLC chromatogram of further degraded products of the released Fmoc-Trp(Boc)-PLGA conjugates described in Figure 4a at pH 9 for 3 day incubation. Note that the elution peak appearing at 39.5 min is authentic Fmoc-Trp(Boc).

Figure 5a shows mass spectra of hydrolyzed products obtained from Fmoc-Trp(Boc)-PLGA oligomer conjugates released in the incubation medium.

Figure 5b shows mass spectra of authentic Fmoc-Trp(Boc).

Figure 6 shows the schematic illustration of drug-

PLGA conjugation system.

Figure 7 shows Gel Permeation chromatogram of doxorubicin conjugated polymer (Solid line) and unconjugated polymer (dotted line).

5 Figure 8 shows transmission electron microscopic pictures of nanoparticles containing doxorubicin-PLGA conjugate. Scale bars in A and B are 2 μ m and 200 nm, respectively.

10 Figure 9 shows release profiles of doxorubicin from nanoparticles encapsulated with free doxorubicin (closed circle) and doxorubicin-PLGA oligomer conjugates from nanoparticles encapsulated with conjugated doxorubicin (open circle). Each data point was obtained from triplicate experiments.

15 Figure 10a shows the reversed phase HPLC result of free doxorubicin.

Figure 10b shows the reversed phase HPLC result of the released fraction from nanoparticles encapsulated with conjugated doxorubicin for 19 days at 37°C.

20 Figure 10c shows the reversed phase HPLC result of the further incubation of the released fraction described in Figure 10b for additional 4 days at 37°C.

Figure 11 shows cytotoxic activity of free doxorubicin (closed square) and the released fraction from nanoparticles containing conjugated doxorubicin (closed triangle) against HepG2 cells. Each data point was obtained from triplicate experiments.

25

Figure 12 shows Gel Permeation chromatogram of doxorubicin-PLGA conjugate via an ester bond.

Figure 13 shows release profiles of doxorubicin from nanoparticles encapsulated with free doxorubicin and doxorubicin-PLGA oligomer conjugates from nanoparticles encapsulated with conjugated doxorubicin via an ester bond.

Figure 14 shows *in vivo* antitumor activity against EL4 cell line of doxorubicin and its polymer nanoparticles.

Detailed Description of the invention

The present invention relates to a sustained controlled release system constructed by the conjugation of drug molecules to the terminal groups of biodegradable polyester polymers via covalent bond, which enable the drugs to be released constantly, with high loading efficiency.

The present invention also relates to the method for preparing system wherein the solvent is selected from the group comprising methylene chloride, N,N-dimethylformamide, dimethylsulfoxide, and tetrahydrofuran.

In accordance with the present invention, the conjugate of target molecules and polymers is formulated into micropospheres, nanoparticles, or films. In the preferred embodiments, micropospheres are

approximately 1 to approximately 300 μm and nanoparticles are about 50 to about 1,000 nm in size.

The present biodegradable polyester polymer may be selected from the group comprising poly(lactic acid),
5 poly(glycolic acid), poly(D-lactic-co-glycolic acid), poly(L-lactic-co-glycolic acid), poly(D,L-lactic-co-glycolic acid), poly(caprolactone), poly(valerolactone), poly(hydroxybutyrate), poly(hydrovalerate), polydioxnanone, and their derivatives.
10 Preferably, The molecular weight range of the biodegradable polyester polymer is from about 1000 Da to about 100000 Da.

Also, the biodegradable polyester polymer is selected from poly (lactic-co glycolic acid) with
15 various compositions (the ratio of lactic acid and glycolic acid, from 1:10 to 10:1) for satisfying the required biocompatibility of the molecule to be delivered including degradation rate and degradation profile.

20

The present invention is based on the conjugation of molecule to be delivered with biodegradable polyester via covalent bond. Covalent bonding structure is defined as follows.

25 Biodegradable polyester polymer has two kinds of functional group, i.e., carboxyl and hydroxy group. The conjugation method, therefore, may be divided into

two groups ; the method wherein the molecules are coupled to carboxyl group of polyester polymer, and the method wherein the molecules are coupled to hydroxy group of polyester polymer. Namely, drug molecules can
5 be covalently conjugated with more than one functional group of polyester polymer. In either method, the drug-polymer conjugate may be formed by appropriate linker or spacer additionally, for coupling or introducing the multifunctional groups, respectively.

10 Moreover, preferably the covalent bond may be formed using multifunctional ligand. In particular, one or more drug molecules may be conjugated to the triglycerol covalently bound to biodegradable polyester polymer. In another preferred embodiment, covalent
15 bond may be formed by conjugating alkyl spacer or other feasible spacer to glycerol or glyceraldehyde.

In case of all mentioned above, the covalent bond between molecules and biodegradable polyester polymers may be ester bond, amide bond, anhydride bond,
20 carbonate bond, urea bond, urethane bond, tioester bond, disulfide bond, imine bond, or carbamate bond, which can or can not be broken down by enzymatic or nonenzymatic degradation.

25 Illustrative examples of molecules that can be used in the system of the present invention include; biologically active compounds such as peptides,

proteins, therapeutic agents, diagnostic agents, and non-biological materials such as pesticides, herbicides, and fertilizers.

Preferably, peptides are selected from the group comprising insulin, calcitonin, ACTH, glucagon, somatostatin, somatotropin, somatomedin, parathyroid hormone, erythropoietin, hypo-thalamic releasing factors, prolactin, thyroid stimulating hormone, endorphins, enkephalins, vasopressin, non-naturally occurring opiods, superoxide dismutase, interferon, asparaginase, arginase, arginine deaminease, adenosine deaminase ribonuclease, trypsin, chemotrypsin, and pepsin.

Therapeutic agent may comprise anticancer agents such as dideoxyinosine, floxuridine, 6-mercaptopurine, doxorubicin, daunorubicin, I-darubicin, cisplatin, etc.; antibiotics such as erythromycin, vancomycin, oleandomycin, ampicillin, etc.; anticoagulant such as heparin; germicides such as ara-A, acrylguanosine, nordeoxyguanosine, azidothymidine, dideoxyadenosine, dideoxythymidine, etc.; antiarrythmic agent; and prodrugs and derivatives thereof.

The present invention also relates to a method for manufacturing the sustained controlled release system.

A method, wherein the conjugation of molecule with polyester polymer is carried out, comprises the steps of;

- 1) activating drug molecule or polymer by mixing with coupling agents, bases, and, if needed, additives;
- 2) conjugating drug molecule with polymer by adding drug molecule to the activated polymer solution of step 1, or by adding polymer to the activated drug molecule solution of step 1;
- 3) purifying polymer-molecule conjugate of step 2.

10 The coupling agent of step 1 may be one or more selected from the group comprising bis(2-oxo-3-oxazolydiny)phosphonic chloride (BOP-Cl), bromo-tris-pyrrolidino-phosphonium hexafluorophosphate (PyBroP), benzotriazole-1-yl-oxy-tris-pyrrolidino-phosphonium

15 hexafluorophosphate (PyBOP), 2-(1H-benzotriazole-1-yl)-1,1,3,3-tetramethyluronium hexafluorophosphate (HBTU), dicyclohexyl carbodiimide, disuccinimidyl carbonate, 1-(3-dimethylaminopropyl)-3-ethylcarbodiimide (EDC), bis(2-oxo-3-oxazolydiny)phosphin, diisopropyl

20 carbodiimide (DIPC), 2-(1H-benzotrioxazolyl)-1,1,3,3-tetramethyl-uronium tetrafluoroborate (TBTU), 2-(5-norboren-2,3-dicarboxyimido)-1,1,3,3-tetramethyluronium tetrafluoroborate (TNTU) and O-(N-succinimidy)-1,1,3,3-tetramethyluronium tetrafluoroborate (TSTU).

25 The base of step 1 may be selected from the groups comprising triethylamine, N-methylmorpholine, pyridine, 1,8-diazabicyclo[5,4,0]-undec-7-ene, N,N-dimethyl

aminopyridine, and N,N-diisopropyl ethylamine.

The additives of step 1 may be one or more selected from the groups comprising hydrobenzotriazole, pentafluorophenol, and N-hydroxy-5-norboren-endo-2,3-
5 dicarboximide.

In this invention, we designed microspheres, nanoparticles, and films by conjugating various target molecules to the terminal end groups of biodegradable polyester microspheres, nanoparticles, and films via a
10 biodegradable ester bond, amide bond, or carbamate linkage to obtain a zero order release kinetic profile. The strategy is that when the conjugated biodegradable polyester chains are randomly hydrolyzed and water soluble fractions are leached out [R.A. Kenley, et al.,
15 *Macromolecules*, **20** (1987) 2398-2403], target drug molecules which were bound to the terminal ends of the cleaved polyester oligomer are released out concomitantly. The drug release rate from the proposed
20 system is expected to be proportional to mass erosion rate of the biodegradable microspheres, nanoparticles, and films. After the release, polyester oligomer chains conjugated to the drug moiety would be further degraded, eventually generating an intact free drug and/or drug with 1-3 polyester oligomer chain.

25 The main advantage of the conjugation of drug to biodegradable polyester is, first to prevent the initial burst and control the sustained release of

molecules from microspheres, nanoparticles, and films.
Second, drug-polymer conjugates are easily formulated
into microspheres, nanoparticles, and films by a single
Oil-in-Water emulsion method with very high
5 encapsulation efficiency (almost 100%).

Practical and presently preferred embodiments of
the present invention are illustrative as shown in the
following Examples.

10 However, it will be appreciated that those skilled
in the art, on consideration of this disclosure, may
make modifications and improvements within the spirit
and scope of the present invention.

15 **Examples**

<Example 1> Coupling molecule to PLGA via covalent bond

(1) Coupling peptide to PLGA via amide bond

Antifungal peptide (PCT-KR 96-0034, KYIVFVFK)
20 filed by this applicant was synthesized by using
automatic 431A peptide synthesizer (Biosystems) through
solid phase synthesis, and then deprotected by
trifluoroacetic acid solution. Purified product was
obtained using reverse phase high performance liquid
25 chromatography (HPLC).

After dissolving PLGA5010 (MW 10,000, lactic
acid:glycolic acid, 1:1 mole ratio) in mixed solvent

including N,N-dimethylformamide and methylene chloride, the above peptide dissolved in a small dose of dimethylformamide was added. Coupling reagent of EDC/HOBt or DCC/HOBt and base of triethylamine were
5 added, and this solution was stirred at room temperature for 12 hours. Reaction process was assayed, using thin layer chromatography and gel permeation chromatography (GPC).

After the reaction was completed, ether was added
10 and the precipitate was dissolved in methylene chloride. This solution was washed with 2 % hydrochloric acid or brine (saturated-NaCl solution). The organic phase was concentrated by using rotary evaporator and lyophilized.

The reaction forming covalent linkage was
15 monitored by gel permeation chromatography, fluorescence analyzer and UV spectrophotometry.

(2) Coupling lysozyme to PLGA via amide bond

PLGA and lysozyme were dissolved in dimethyl
20 sulfoxide (DMSO), followed by adding coupling agents of DCC and HOBt and the solution was stirred at room temperature. Diethyl ether was added to precipitate the product.

The progress of reaction was monitored by gel
25 permeation chromatography and fluorescence analyzer.

<Example 2> Coupling molecule to activated PLGA via

covalent bond

(1) Method for activating PLGA : Synthesis of p-nitrophenyl carbonate of PLGA

p-nitrophenyl chloroformate was dissolved in dried
5 methylene chloride, and then temperature was lowered to
0 °C. PLGA5010 dissolved in dried methylene chloride
was added to the above solution. Pyridine was added
and stirred at 0 °C for 30 minutes, then further
stirred at room temperature for 1 ~ 3 hours or stirred
10 at 0 °C for 3 ~ 6 hours. Precipitate was formed with
ether.

By precipitation using ether and methylene
chloride, product was purified and characterized by
gel permeation chromatography and UV spectrum.

15

(2) Coupling antifungal peptide with activated PLGA

Antifungal peptide dissolved in dimethylformamide
was slowly added to polymer solution of the above step
1. Triethylamine was added to the solution and stirred
20 at room temperature for 6 ~ 24 hours. Reaction process
was monitored, using gel permeation chromatography, UV
spectrum, and fluorescence analyzer.

After the reaction was completed, ether was added
to remove dimethylformamide and the precipitate was
25 dissolved in methylene chloride. This solution was
washed with 2 % hydrochloric acid or brine, and the
organic phase was concentrated by rotary evaporator,

and then lyophilized.

The conjugates were characterized by gel permeation chromatography, fluorescence analyzer, and UV spectrophotometry.

5

(3) Coupling amphotericin B to activated PLGA

Amphotericin B dissolved in dimethyl sulfoxide was slowly added to polymer solution of above step 1, and then stirred at room temperature for 6 ~ 24 hours. by
10 gel permeation chromatography and thin layer chromatography, the reaction process was monitored.

After the completion of the reaction, ether was added to the solution, followed by centrifugation at 3,000 rpm for 15 minutes. The resulting precipitate
15 was dissolved in methylene chloride and filtrated, and then the filtrate was concentrated. After dissolving the filtrate in methylene chloride, it was washed with water. The organic phase was concentrated by rotary evaporator and dried.

20

(4) Coupling doxorubicin with activated PLGA

Poly(D,L-lactic-co-glycolic acid) having lactic/glycolic molar ratio of 50/50 was obtained from Wako Chemicals (Japan). [PLGA5005]. The average
25 molecular weight was 8,020 as determined from gel permeation chromatography. This polymer has free hydroxyl and carboxylic groups at its terminal ends.

Doxorubicin, and p-nitrophenyl chloroformate were obtained from Sigma. All other chemicals were analytical grade.

One gram of PLGA dissolved in 10 ml of methylene chloride was activated by 72 mg of p-nitrophenyl chloroformate by adding 47 mg of pyridine (PLGA/p-nitrophenyl chloroformate/pyridine stoichiometric molar ratio: 1/2.8/4.8) in a dropwise manner into the solution at 0°C. The reaction was carried out for 3 hr at room temperature under nitrogen atmosphere. The reaction progress was monitored by gel permeation chromatography (GPC) with dual UV detection at 230 nm and 260 nm for ester group in the PLGA backbone and p-nitrophenyl group in the activated PLGA end group, respectively. The resultant solution was diluted by methylene chloride and washed with 0.1% HCl and brine solution. The organic phase was separated, dried on sodium sulfate, and then dried under vacuum (yield: 80 %). The activated PLGA (0.1 g) dissolved in 3 ml of dimethylformamide (DMF) was reacted with 6.3 mg of doxorubicin in the presence of 5 mg of triethylamine for 24 hrs at room temperature under nitrogen atmosphere (stoichiometric molar ratio of activated PLGA/doxorubicin/triethylamine: 1/0.8/4). The progress of doxorubicin conjugation to activated PLGA was monitored by GPC by an UV-Vis dual wavelength at 230 nm and 480 nm which detected the fraction of PLGA and

doxorubicin conjugated PLGA, respectively. The precipitated product by the addition of cold diethyl ether was filtered and dried. The yield of conjugation reaction was 58%. The extent of doxorubicin
5 conjugation to PLGA was determined by dissolving the conjugate in dimethylsulfoxide (DMSO), and then its absorbance was measured at 480 nm. A series of doxorubicin with different concentrations in DMSO were used as calibration standards.

10

(5) Gel Permeation Chromatography (GPC) of Doxorubicin-PLGA Conjugates

The synthesized conjugates were characterized by GPC using Gilson 306 pump with UV-Vis detector. The
15 GPC column was Shodex K-803 (300 x 7.8 mm, Phenomenex, USA) and tetrahydrofuran was used as a mobile phase with a flow rate of 1 ml/min. Molecular weight of the conjugate was calculated using a series of polystyrene standards (Mr: 114,200, 44,000, 13,700, and 3,700).
20 The PLGA-doxorubicin conjugate was analyzed by gel permeation chromatography as shown in Figure 7. The conjugated PLGA was eluted earlier than the unconjugated PLGA, supporting that doxorubicin was conjugated to PLGA. Average molecular weight of the
25 conjugate was 9,210 and that of PLGA was 8,020, respectively. The slight increase in molecular weight was due to the doxorubicin conjugation and the removal

of low molecular weight PLGA fraction in the process of purification of doxorubicin-PLGA conjugate. From the GPC profile, it was confirmed that free doxorubicin was completely removed from the synthesized PLGA-doxorubicin conjugate.

<Example 3> Coupling activated molecule to PLGA via covalent bond

10 Coupling Fmoc-Trp(Boc) to PLGA via ester bond

(1) Coupling Reaction of Fmoc-Trp(Boc) to PLGA

Various coupling reagents and reaction conditions were studied in the conjugation of various molecules into polyester polymer. First, different coupling reactions were explored by employing various coupling agents for Poly(D,L-lactic-co-glycolic acid) (PLGA) 50/50 to maximize the conjugation yield. Poly(D,L-lactic-co-glycolic acid) (lactic acid/glycolic acid ratio, 75/25 and 50/50) were purchased from Wako Pure Chemical Industries Ltd (PLGA 5010 and 7510). The two PLGA polymers with 75/25 and 50/50 lactic/glycolic monomer composition ratios had average molecular weight (MW) of 9,800 and 8,700, respectively, as determined by gel permeation chromatography. The PLGA polymer used in this reaction had an uncapped free carboxylic acid group at one terminal end and a hydroxyl group at the other end. Typically, Fmoc-Trp(Boc) (80 mg, 1.5×10^{-4}

mole) dissolved in CH_2Cl_2 (3 ml) under nitrogen atmosphere was mixed with various combinations of coupling reagents (1.5×10^{-4} mole) and bases (1.5×10^{-4} mole). PLGA with lactic/glycolic acid 50/50 ratio (0.43 g, 5×10^{-5} mole) dissolved in 7 ml of CH_2Cl_2 was then added to the solution. The coupling reaction was carried out at room temperature for 4-6 hrs. The resulting solution was diluted with the addition of 20 ml CH_2Cl_2 and washed with brine. An organic layer was separated, concentrated, and dried under vacuum. The conjugated Fmoc-Trp(Boc)-PLGA was further purified by the following precipitation procedure. The product mixture dissolved in 2 ml CH_2Cl_2 was precipitated by the addition of 30 ml diethyl ether. This precipitation was repeated three times. The separation of unconjugated free Fmoc-Trp(Boc) from a mixture of Fmoc-Trp(Boc)-PLGA conjugate and unreacted PLGA was confirmed by gel permeation chromatography (GPC). The conjugate was lyophilized and stored at -20°C until use.

Coupling reagents, 2-(1H-benzotriazole -1-yl)-1,1,3,3-tetramethyluronium hexafluorophosphate (HBTU), N-hydroxybenzotriazole (HOBt), benzotriazole-1-yl-oxy-tris-pyrrolidino-phosphonium hexafluorophosphate (PyBOP), and bromo-tris-pyrrolidino-phosphonium hexafluorophosphate (pyBroP) were obtained from Novabiochem. Bis(2-oxo-3-oxazolidinyl)-phosphonic chloride (BOP-Cl) was purchased from Advanced Chemtech.

1-(3-dimethylaminopropyl)-3-ethylcarbodiimide (EDC), tetrahydrofuran (THF), methylene chloride (anhydrous), diethyl ether (anhydrous), triethylamine (TEA), polyvinylalcohol (PVA, 88 % hydrolyzed, MW 25,000) and
 5 4-dimethylaminopyridine (DMAP) were obtained from Aldrich. All other reagents were analytical grade and used without further purification.

Table 1

10 Synthesis of Fmoc-Trp (Boc)-PLGA (50/50)

Mole ratio of PLGA : Fmoc-Trp (Boc)	Coupling reagent	Base or additive	Reaction time	Conjugation percent
1:3	BOP-Cl	TEA	4h	No reaction
1:10	BOP-Cl	TEA	6h	< 10%
1:3	EDC	HOBt	4h	< 10%
1:3	EDC	HOBt	6h	< 10%
1:3	PyBOP	TEA	4h	37%
1:3	HBTU	TEA	4h	20%
1:3	PyBroP	TEA	4h	60%
1:3	PyBroP	TEA	6h	63%
1:3	PyBroP	DMAP	4h	63%

As shown in Table 1, various coupling agents and bases in different combinations were used to provide Fmoc-Trp(Boc)-PLGA conjugate in different yield. The conjugation percent was mainly dependent on the kind of coupling agents. Among the reaction conditions tested, PyBroP/TEA combination resulted in the greatest conjugation percent of 63 % in PLGA 50/50. Thus, the PyBroP/TEA combination was also used for the conjugation of PLGA 75/25. The conjugation percent of Fmoc-Trp(Boc) to PLGA 75/25 was 46 %. Figure 1 shows GPC profiles of PLGA 50/50 and Fmoc-Trp(Boc)-PLGA 50/50 conjugate. It can be seen that the conjugate was eluted slightly earlier than the unconjugated PLGA due to the additional presence of Fmoc-Trp(Boc) group in one end terminal of PLGA chain. It should be mentioned that the elution peak of the conjugate monitored at 267 nm does not reflect a fraction of unconjugated PLGA that was not detected at that wavelength. Elemental analysis data (calculated C 47.3 %, H 4.73 %, N 0.19 %, and O 47.8 %; measured C 47.0 %, H 4.6 %, N 0.2 %, and O 48.2 %) support the conjugation percent of 63%.

(2) Characterization of Fmoc-Trp(Boc)-PLGA

The conjugates were characterized by GPC using Gilson 306 pump with UV detector. The GPC column was Shodex K-803 (300 x 7.8 mm, Phenomenex) and THF was used as a mobile phase with a flow rate of 1 ml/min.

The eluted conjugate was monitored by UV at dual wavelengths (230 nm for PLGA and 267 nm for Fmoc group). Average molecular weight of the conjugate was calculated using a series of polystyrene standards (Mr: 114,200, 44,000, 13,700, and 3,700). The conjugation was confirmed by measuring fluorescence of Fmoc-Trp(Boc)-PLGA (excitation at 295 nm and emission at 355 nm for Trp group and excitation at 260 nm and emission at 305 nm for Fmoc group). The conjugation percent of Fmoc-Trp(Boc) to PLGA was determined by measuring absorbance of Fmoc-Trp(Boc)-PLGA in THF at 267 nm using a series of Fmoc-Trp(Boc) with a different concentrations as standards. The conjugation percent was calculated as a relative molar ratio of Fmoc-Trp(Boc) conjugated PLGA compared to the total PLGA amount in the sample.

Coupling Doxorubicin to PLGA via ester bond

(1) Preparation of Fmoc-Doxorubicin

Dox HCl salt (50 mg, 86 μ mole) was dissolved in N, N-dimethylformamide (DMF) (2 ml), and Fmoc-OSu (30 mg, 90 μ mole) was added, followed by adding 30 μ l (172 μ mole) of N,N-diisopropylethylamine. After 3 h, the solvent was evaporated *in vacuo*, and the residue was crystallized by trituration from 0.1 % aqueous trifluoroacetic acid (TFA) (vol/vol). The crystals were collected by filtration and washed once with cold

diethyl ether to remove the trace of excess Fmoc-OSu. After freeze drying, 55 mg of 98 % pure N-Fmoc-Dox was obtained (84% yield).

5 (2) Conjugation of Fmoc-Dox and PLGA5005

PLGA5005 (0.18 g) and Fmoc-Dox (20 mg) were dissolved in CH_2Cl_2 (10 ml). PyBroP (15.6 mg), triethylamine (TEA) (20 μl), and dimethylaminopyridine (DMAP) (4.5 mg) were added to stirred solution under
10 nitrogen. After 15 hrs, reaction mixture was diluted with CH_2Cl_2 (20 ml). Organic layer was washed with 5% aqueous HCl solution (x 2) and brine (x 2). Organic layer was concentrated under vacuum. Conjugation between Fmoc-Dox and PLGA was monitored by GPC and UV-
15 Vis detector (480 nm for Dox, 267 nm for Fmoc, 230 nm for PLGA).

(3) Deprotection of Fmoc group in Fmoc-Dox-PLGA conjugate

20 Fmoc-Dox-PLGA conjugate was dissolved in DMF (3 ml) and 300 μl of piperidine was added. After 5 min, the reaction mixture was placed in an ice bath and acidified by the addition of a mixture containing a 300 μl of TFA, 700 μl of pyridine, and 2 ml of DMF. The
25 solvent was evaporated *in vacuo*. The residue was solidified by trituration from the addition of diethyl ether in DMF. The solids were dissolved in CH_2Cl_2 (30

ml) and washed with 5% HCl aqueous solution and brine. Organic layer was concentrated under vacuum. The solid was purified by the precipitation method using diethyl ether.

5

<Example 4> Preparation and characterization of Microsphere with the conjugate Fmoc-Trp(Boc) to PLGA

(1) Microsphere Preparation

10 PLGA microspheres containing Fmoc-Trp(Boc)-PLGA conjugates were prepared by an oil-in-water (O/W) single emulsion technique. Four different formulations were prepared as listed in Table-2. One hundred mg of Fmoc-Trp(Boc)-PLGA conjugates [PLGA 50/50 (formulation
15 A), a 50:50 mixture of PLGA 50/50 and 75/25 (formulation B), and PLGA 75/25 (formulation C)] and 400 mg of PLGA 50/50 were dissolved in a co-solvent mixture of 2.5 ml of DMSO and 2.5 ml of methylene chloride. As control microspheres (formulation D), 10
20 mg of free Fmoc-Trp(Boc) and 490 mg of PLGA 50/50 were used for the formulation. The resulting solutions were emulsified in 500 ml of 0.3 % (w/v) PVA / phosphate buffered saline (PBS) solution for 20 min by homogenization at 6,000 rpm using a PowerGen 700
25 (Fisher Scientific) and subsequently stirred magnetically for 3 hrs at room temperature to extract DMSO and evaporate methylene chloride. The hardened

microspheres were collected by centrifugation at 8,000 rpm for 20 min, washed twice with deionized water, and then lyophilized.

5 Table 2

Formulation of Microspheres

Formula- tion	PLGA 50/50 Weight (mg)	Fmoc-Trp (Boc)-PLGA, Weight (mg)	Encapsulation Efficiency, %	Average Size (μ m)
A	400	100 ^a	100	8.76 (1.2)
B	400	100 ^b	100	8.33 (0.9)
C	400	100 ^c	100	8.52 (1.7)
D	490	10 ^d	20.1	8.62 (1.6)

a. Fmoc-Trp(Boc)-PLGA 50/50 conjugate

b. Fmoc-Trp(Boc)-PLGA 75/25 conjugate

10 c. A 1:1 mixture of Fmoc-Trp(Boc)-PLGA 50/50
conjugate and Fmoc-Trp(Boc)-PLGA 75/25 conjugate

d. Free Fmoc-Trp(Boc)

The Fmoc-Trp(Boc)-PLGA conjugates with different
15 copolymer compositions of 50/50 and 75/25 mixed with
PLGA 50/50 was formulated into microspheres using a
single oil-in-water emulsion method as shown in Table 2.
The microspheres (formulations A, B, and C) containing
the Fmoc-Trp(Boc)-PLGA conjugates exhibit almost 100 %
20 encapsulation efficiencies owing to their limited
solubility in water, whereas conventionally prepared

microspheres (formulation D) encapsulated with unconjugated Fmoc-Trp(Boc) show only 20.1 % encapsulation efficiency due to the diffusion of moderately water soluble Fmoc-Trp(Boc) into the aqueous phase during the solvent evaporation procedure.

(2) Scanning Electron Microscopy and Particle Size Distribution

Microsphere shape and surface morphology were estimated using a scanning electron microscopy (SEM, Philips 535M). Freeze-dried microspheres were mounted on an aluminum stub covered with a carbon adhesive tape and then coated with gold. Size average and distribution of microspheres were determined by a Coulter Counter (CASYTM, Scharfe System, Germany). Microspheres suspended in isotonic saline solution were forced to flow through a capillary. The resistance change by a particle was electronically scaled and counted. SEM pictures indicate spherical shaped microspheres having a very smooth surface morphology. There were no apparent discrepancies in morphologies between conjugated and unconjugated Fmoc-Trp(Boc) containing microspheres. All the microspheres have their average size in diameter between 8.33 and 8.76 μm .

<Example 5> Fmoc-Trp(Boc)-OH and its polyester oligomer release from polymer microsphere

(1) *In vitro* Release Study

One hundred mg of freeze-dried microspheres were suspended in 30 ml of 0.033 M PBS (phosphate buffer saline) at pH 7.0 containing 0.01 % sodium azide. They were incubated in a polypropylene tube at 37°C under static condition. At predetermined intervals, the supernatant from each tube was collected by centrifugation at 8,000 rpm for 30 min and replaced with an equal volume of fresh buffer medium. The supernatant was frozen and stored at -20 °C until analyzed.

(2) Determination of Fmoc-Trp(Boc) Concentration in Release Medium

The Fmoc-Trp(Boc) concentration in the release medium was determined by measuring fluorescence intensity with a spectrofluorometer (RF-5301PC, Shimadzu, Japan) with an excitation at 295 nm and an emission at 314 nm. A standard calibration curve was constructed by dissolving 10 mg of free Fmoc-Trp(Boc) in 2 ml of acetonitrile and diluting it with excessive PBS buffer solution (pH 8). For the evaluation of cumulative release percent, the microspheres after incubation for 31 days were freeze-dried and the amount of unreleased Fmoc-Trp(Boc) in the microspheres was determined. Ten mg of dry microspheres dissolved in 1

ml of 0.1 N NaOH solution was incubated at 37 °C for 2 days. The remaining amount of Fmoc-Trp(Boc) was then determined. Osmolality build-up in the release media was measured by a freezing point osmometer (model A0300, 5 Knauser, Germany).

(3) Identification of Released Products from Microsphere Containing Fmoc-Trp(Boc)-PLGA Conjugates

Released products from the microspheres 10 encapsulated with Fmoc-Trp(Boc)-PLGA conjugate and free Fmoc-Trp(Boc) were separated by a C₁₈ reversed phase column by high performance liquid chromatography (HPLC) and the elution was monitored by fluorescence (excitation 260 nm, emission 305 nm). The released 15 Fmoc-Trp(Boc)-PLGA oligomer conjugates were further incubated in 0.033 M sodium phosphate buffer (pH 9) at 37°C for additional 3 days to see whether authentic free molecule of Fmoc-Trp(Boc) was regenerated. This was performed by fractional separation of the 20 conjugates in HPLC followed by taking its mass spectrum. The mass spectrometer (Platform II, Micromass, UK) was operated in a positive ion mode.

(4) Degradation Study

Figure 2 shows release profiles of Fmoc-Trp(Boc)- 25 PLGA oligomer conjugates in the incubation medium from various microsphere formulations. It can be seen that the microspheres conjugated with Fmoc-Trp(Boc)

exhibited constant release profiles over 20 days with an initial, short lag time period. On the other hand, the microspheres containing unconjugated Fmoc-Trp(Boc) showed a rapid release in the initial incubation stage, resulting in the early termination of release within 5 days. The microspheres (formulation A) containing Fmoc-Trp(Boc) conjugated with relatively fast degrading PLGA 50/50 polymer released their degradation products, Fmoc-Trp(Boc)-PLGA oligomer conjugates, faster than those (formulation B) conjugated with slowly degrading PLGA 75/25. Although their release rates did not differ greatly due to the relative small incorporation percentage of the conjugates in microspheres, this finding reveals that release kinetic rates of the drug conjugated with PLGA, indeed, can be judiciously controlled by appropriately selecting various PLGA polymers that degrade in different rates. Therefore, molecular weight and/or copolymer composition of PLGA to be conjugated would be an important variable to control the release rate in the present system. The formulation C having a 50:50 blend mixture composition of PLGA 50/50 and PLGA 75/25 in the Fmoc-Trp(Boc) conjugation demonstrates an intermediate release kinetic rate between the two release rates of formulations A and B, supporting our hypothesis that the chemical degradation rate of conjugated PLGA chains modulates the liberation rate of water solubilizable

Fmoc-Trp(Boc)-PLGA oligomer fraction into the incubation medium as mentioned earlier.

Figure 3 shows pH and cumulative osmolality changes in the incubation medium as a function of time. Since the incubation medium was completely replaced by fresh buffer solution at every sampling period, there were insignificant pH variations during the release period, while the continuous build-up of osmolality by the accumulation of water soluble PLGA degradation products in the medium was observed. This suggests that the release of degradation products from the PLGA 50/50 microspheres is a linear function of time [G. Crotts, et al., *J. Controlled Release*, **47** (1997) 101-111]. Initially increased osmolality upon incubation can be attributed to the preferential diffusion of pre-existing small molecular weight PLGA oligomer fragments generated during the microsphere formulation process.

Figure 4 shows the reversed phase HPLC results obtained from the released Fmoc-Trp(Boc)-PLGA conjugates in the medium from the formulation A microspheres at day 7. The released conjugates are expected to have a mixture of molecular species composed of Fmoc-Trp(Boc) linked with different chain lengths of water soluble PLGA oligomers resulting from the random cleavage of PLGA chain. The HPLC result, however, demonstrates that the released Fmoc-Trp(Boc)-PLGA oligomer conjugates in the buffer medium were

eluted earlier as a major single peak than the authentic Fmoc-Trp(Boc), although many other small unidentified peaks followed can also be seen. Further incubation of the released Fmoc-Trp(Boc)-PLGA oligomer conjugates in the buffer medium permitted the regeneration of intact Fmoc-Trp(Boc) peak as a result of chain scission of PLGA oligomers attached to Fmoc-Trp(Boc). This was additionally confirmed by mass spectroscopy. As shown in Figure 5, the major product from the additional incubation of the released Fmoc-Trp(Boc)-PLGA oligomers was identified as Fmoc-Trp(Boc) by its mass spectrum which shows $[M+K]^+$ and $[M+H+K]^{2+}$ ion peak at $m/z = 563.38$ (calculated 565) and $m/z = 282.19$ (calculated 283). Comparison of mass spectrum relative to that of intact Fmoc-Trp(Boc) indicates that the major components released from the microspheres were Fmoc-Trp(Boc)-PLGA oligomer conjugates and intact molecule of Fmoc-Trp(Boc) could be regenerated by further degradation

It has been demonstrated that drug molecules could be delivered in a zero order fashion from biodegradable microspheres in a desired time span by the conjugation approach of a drug to PLGA chain end via an ester linkage. A schematic illustration of the proposed drug-PLGA conjugate system is depicted in Figure 6. This strategy can be potentially applied to a wide range of hydrophilic drugs like antibiotics to

improve their therapeutic effectiveness which require an extended duration of release at the injection site *in vivo*.

5 **<Example 6> Preparation and characterization of nanoparticle with the conjugate of Doxorubicin and PLGA via carbamate bond**

Two types of nanoparticles containing doxorubicin-
10 PLGA conjugate and free doxorubicin were prepared by a spontaneous emulsion solvent diffusion method. One hundred mg of PLGA-doxorubicin conjugate dissolved in 10 ml of acetone was slowly added to 100 ml of deionized water containing 1 % (w/v) Pluronic F-127
15 under vigorous stirring condition. For the encapsulation of free doxorubicin into nanoparticles, 95 mg of PLGA and 5 mg of doxorubicin were co-dissolved in acetone and then used. The nanoparticles formed in the aqueous solution were collected by
20 ultracentrifugation (Beckman, USA) at 15,000 rpm for 1 hr and resuspended in phosphate buffered saline (PBS) solution. The resuspended nanoparticles were stored under frozen condition (-20°C) until use. The loading amount of doxorubicin within nanoparticles was
25 determined by a spectroscopic method. A known amount of freeze dried nanoparticles was completely dissolved in dimethylsulfoxide (DMSO) and then the absorbance was

measured at 480 nm according to the aforementioned method. Encapsulation efficiency was calculated based on the percent ratio of the amount of doxorubicin incorporated into nanoparticles to the initial amount used. Size distribution was measured by using a laser light scattering technique (ZetaPlus, Brookhaven Instrument Corp., USA). Transmission electron microscopy (TEM) picture was taken without a heavy metal staining procedure (CM20 Microscoppr TEM, Philips). Figure 8 shows transmission electron microscopy (TEM) picture of doxorubicin-PLGA conjugate encapsulated nanoparticles prepared by the spontaneous emulsion solvent diffusion method. The nanoparticles were unaggregated while maintaining an individual spherical shape. Average diameter and zeta potential of nanoparticles, as determined by a laser scattering method, was 269.7 nm and -58.1 mV for the free doxorubicin encapsulated nanoparticles, and 356.0 nm and -86.6 mV for the doxorubicin-PLGA conjugate encapsulated nanoparticles, respectively. The loading percent of free doxorubicin within nanoparticles was 0.26 % (w/w) with 6.7 % of loading efficiency. On the other hand, the doxorubicin-PLGA conjugate nanoparticles had 3.45 % (w/w) loading percent with 96.6 % efficiency. The remarkably enhanced loading percent as well as its concomitantly improved efficiency for the nanoparticles containing the

conjugate were clearly due to the fact that the doxorubicin-PLGA conjugate became water insoluble while free doxorubicin was moderately water soluble.

5 **<Example 7> Characterization of release molecule from nanoparticle with the conjugate of Doxorubicine and PLGA via carbamate bond**

(1) Release Experiment

10 Twenty mg of nanoparticles suspended in 20 ml of PBS buffer was sealed in a dialysis bag (M.W. cutoff: 10,000, Spectrapor). The dialysis bag was incubated in 30 ml of PBS buffer at 37°C. The released doxorubicin in the incubation medium was collected at pre-
15 determined time intervals and stored frozen for quantitative analysis. The release amount was analyzed at 480 nm.

(2) Reversed Phase High Performance Liquid
20 Chromatography (HPLC)

 The released doxorubicin and its PLGA oligomer conjugates in the medium was analyzed by a HPLC system (Waters 486) with detection at 480 nm, using the following operation conditions; PRP-3 column (4.1 mm x
25 150 mm, Hamilton) as a reversed phase column, a linear gradient elution of water/acetonitrile from 95/5 to 50/50; a mobile phase flow rate of 1 ml/min.

(3) Degradation Study

Release profiles of doxorubicin from the two nanoparticles were compared as shown in Figure 9. The release profile of the free doxorubicin encapsulated nanoparticles exhibits a very rapid release of doxorubicin in the early incubation stage, whereas that from the conjugate encapsulated nanoparticles shows a sustained release behavior over an extended period. It should be noted that the nanoparticles containing the doxorubicin-PLGA conjugate released a mixture species of doxorubicin-PLGA oligomer conjugates because the carbamate linkage between doxorubicin and PLGA was not easily cleaved in the aqueous medium. The sustained release action was caused by the gradual chemical degradation of conjugated PLGA backbone and subsequent controlled liberation of water soluble doxorubicin-PLGA oligomer conjugates in the incubation medium. Their release rate was solely dependent on how fast the conjugated PLGA chains were hydrolyzed to reach the critical MW. The released fraction from the nanoparticles collected for 19 days incubation was subjected to reversed phase HPLC analysis as shown in Figure 10. The released fraction contained a major peak and other later eluting small peaks, which were likely to be a mixture of water soluble doxorubicin-PLGA oligomer conjugates. The ester linkage adjacent to

glycolic acid unit in the PLGA chain is more susceptible to hydrolysis than that to lactic acid unit, resulting in the production of non-randomly cleaved PLGA oligomer species enriched with lactic acid.

5 Further incubation of the released fraction at 37°C for 3 additional days resulted in the growth of the major peak with concomitant disappearance of the other small peaks. This suggests that the conjugated PLGA oligomers further degraded until one or two lactyl or

10 glycolic monomer unit be still conjugated to doxorubicin via a stable carbamate linkage.

(4) *In vivo* cytotoxicity assay

Cytotoxicities of doxorubicin and its PLGA oligomer conjugates released from nanoparticles were determined against human hepatoblastoma cell line (HepG2) obtained from Korea Research Institute of Bioscience and Biotechnology. Free doxorubicin and the released fraction from nanoparticles for 19 days

15 incubation were used for determining the inhibition of cell growth using a tetrazolium dye (MTT) assay according to the previously established method [R. I. Freshney, *Measurement of Viability and Cytotoxicity*, Chapter 19 in *Culture of Animal Cells*, Third Edition.,

20 Wiley-Liss Inc., New York, 1994, pp. 287-307]. Dulbecco's modification of Eagle's MEM (DMEM) was used as a major cell growth medium and a humidified

atmosphere (5 % CO₂) was maintained for cell culture. HepG2 cells harvested in a logarithmic growth phase were seeded on 96 wells at a cell density of 5×10^3 cells/ml. After incubating the cells in a logarithmic
5 phase with various concentrations of free doxorubicin and the released fraction for 72 hrs, the MTT assay was performed and the percentage of cell viability was then determined.

10 The released fraction from the nanoparticles was tested whether a mixture of doxorubicin-PLGA oligomer conjugates still retained anti-cancer drug activity. Figure 11 shows HepG2 cell viabilities against the released fraction from nanoparticles and free
15 doxorubicin used as a positive control. It can be seen that the overall cytotoxic effect of the released fraction was slightly lower than that of free doxorubicin, presumably due to the presence of uncleaved PLGA oligomers conjugated to doxorubicin.
20 The IC₅₀ value of the released fraction was 13.7 μ M and that of free doxorubicin was 8.9 μ M. In the literature, the reported IC₅₀ value of free doxorubicin was 7.3 μ M [E.B. Yang, et al., *Cancer Letter*, 117: 93-98 (1997)]. Since a mixture of doxorubicin-PLGA oligomer conjugates
25 might have different cytotoxic activities depending on the chain length of uncleaved PLGA conjugated to doxorubicin, the above value should be regarded as an

average cytotoxic activity for the released fraction during the study period.

5 **<Example 8> Characterization of released molecule from nanoparticles with the conjugate of Doxorubicin and PLGA via an ester bond**

(1) Release Experiment

10 Twenty mg of nanoparticles suspended in 20 ml of PBS buffer was sealed in a dialysis bag (M.W. cutoff: 10,000, Spectrapor). The dialysis bag was incubated in 30 ml of PBS buffer at 37°C. The released doxorubicin in the incubation medium was collected at pre-
15 determined time intervals and stored frozen for quantitative analysis. The release amount was analyzed at 480 nm.

(2) Degradation Study

20 Fig 12 shows GPC profile of PLGA and its conjugated with doxorubicin via an ester bond. It can be seen that chemically conjugated PLGA has the absorbance at 480 nm, the characteristic wavelength of doxorubicin but free PLGA did not, which confirmed the
25 success of the conjugation of doxorubicin with PLGA in chemically conjugated PLGA.

Release profiles of doxorubicin from the two nanoparticles were compared as shown in Figure 13. The release profile of the free doxorubicin encapsulated nanoparticles exhibited a very rapid release of doxorubicin in the very early incubation stage whereas that of doxorubicin chemically conjugated nanoparticles showed the comparatively slow release of doxorubicin and its PLGA oligomer in the early incubation stage. Theoretically, the release profile of doxorubicin chemically conjugated nanoparticles was expected to exhibit sustained release kinetics in the entire stage because the release was mainly controlled by mass erosion rate of the polymer. However, in this case, the molecular weight of biodegradable PLGA conjugated with doxorubicin was much lower than that of PLGA encapsulating doxorubicin because the harsh deprotection step of Fmoc-Doxorubicin hydrolyzed the polymer resulting in the preparation of low molecular weight of PLGA conjugated with Doxorubicin. Considering the low MW of conjugated polymer, the initial rapid release of doxorubicin was due to the high solubility of low molecular weight of PLGA and its hydrolyzed oligomer in early incubation stage.

(3) *In vivo* antitumor activity assay

Antitumor activity against solid tumor of free doxorubicin, free PLGA, doxorubicin encapsulated in

nanoparticles and doxorubicin conjugated with nanoparticles was evaluated with mouse EL4 thymoma cells. EL4 Cells (2×10^4 cells in 0.1 ml of PBS pH 7.4 buffer) were transplanted into C57BL16 female mice
5 (10 weeks old) subcutaneously on day 0 and drug injection started on day 10, when tumor diameter reached approximately 2 mm.

The mice were divided into five different groups, each group consisting of 6 mice. The first group,
10 control group, was s.c. injected 100 μ l PBS pH 7.4 daily during 12 days and the second group free doxorubicin (240 μ g/kg body weight). However, the third group was s.c. injected placebo microsphere daily in the first two days, the fourth group nanoparticle
15 conjugated with doxorubicin (2.4 mg/kg body weight) and the fifth group, doxorubicin encapsulated in nanoparticle (1.2 mg/kg body weight).

Fig. 14 shows *in vivo* antitumor activity against
20 EL4 cell line. Tumor diameter from the day of the first injection is plotted as the function of the day after injection of drug and its PLGA formulation. Daily injection of the free doxorubicin (240 μ g/kg) during 12 days showed the significant tumor growth
25 inhibition whereas daily injection of PBS buffer (pH 7.4) did not show any inhibition. Also no antitumor effect was observed for the mice group injected placebo

PLGA nanoparticles. Antitumor effect was observed for two mice groups injected nanoparticles physically entrapping doxorubicin and chemically conjugated with doxorubicin. Interestingly, just daily injection of nanoparticle chemically conjugated with doxorubicin in the first two days shows a little better antitumor activity than that of doxorubicin physically entrapped nanoparticle and a comparable antitumor activity to the daily injection of free doxorubicin in 12 days.

10

What is Claimed is :

1. A sustained controlled release system wherein the drug molecules to be released are conjugated to biodegradable polyester polymers via covalent bond.

5

2. The system of claim 1, wherein the conjugate of drug molecules with biodegradable polyester polymer is formulated into microspheres, nanoparticles, or films.

10

3. The system of claim 2, wherein the microspheres are about 1 to about 300 μm in size.

4. The system of claim 2, wherein nanoparticles are about 50 to about 1000 nm in size.

15

5. The system of claim 1, wherein the biodegradable polyester polymer is selected from the group comprising poly(lactic acid), poly(glycolic acid), poly(D-lactic-co-glycolic acid), poly(L-lactic-co-glycolic acid), poly(D,L-lactic-co-glycolic acid), poly(20 caprolactone), poly(valerolactone), poly(hydroxybutyrate), poly(hydrovalerate), polydioxnanone, and their derivatives.

25

6. The system of claim 1, wherein the biodegradable polyester polymer is selected from the biodegradable polyester polymers of which molecular

weight range is from about 1000 Da to about 100000 Da.

7. The system of claim 1, wherein the biodegradable polyester polymer is selected from poly
5 (lactic-co glycolic acid) with the ratio of lactic acid and glycolic acid from 1:10 to 10:1.

8. The system of claim 1, wherein the conjugation of molecules to biodegradable polyester polymers is
10 employed via ester bond, amide bond, anhydride bond, carbonate bond, imine bond, thioester bond, urea bond, urethane bond, disulfide bond, or carbamate bond.

9. The system of claim 1 or claim 8, wherein the
15 conjugation is carried out by direct bonding of the specified moiety to one another, or else indirect bonding with additional moiety such as a bridge, spacer, or linkage moiety.

20 10. The system of claim 1, wherein the molecules are selected from the biologically active compounds comprising peptides, proteins, therapeutic agents, diagnostic agents, and non-biological materials such as pesticides, herbicides, and fertilizers.

25

11. The system of claim 10, wherein the peptides are selected from the group comprising insulin,

calcitonin, ACTH, glucagon, somatostatin, somatotropin, somatomedin, parathyroid hormone, erythropoietin, hypothalamic releasing factors, prolactin, thyroid stimulating hormone, endorphins, enkephalins, vasopressin, non-naturally occurring opioids, superoxide dismutase, interferon, asparaginase, arginase, arginine deaminase, adenosine deaminase ribonuclease, trypsin, chemotrypsin, and pepsin.

10 12. The system of claim 10, wherein the therapeutic agents comprise anticancer agents such as dideoxyinosine, floxuridine, 6-mercaptopurine, doxorubicin, daunorubicin, I-darubicin, cisplatin, methotrexate, etc.; antibiotics such as erythromycin, 15 vancomycin, oleandomycin, ampicillin, etc.; anticoagulant such as heparin; germicides such as ara-A, acrylguanosine, nordeoxyguanosine, azidothymidine, dideoxyadenosine, dideoxythymidine, etc.; antiarrhythmic agent; and prodrugs and derivatives thereof.

20

13. A method for manufacturing the system of claim 1, comprising the steps of;

- 25 1) activating drug molecule or polymer by mixing with coupling agents, bases, and, if needed, additives;
- 2) conjugating drug molecule with polymer by adding drug molecule to the activated polymer

solution of step 1, or by adding polymer to the activated drug molecule solution of step 1;

3) purifying polymer-molecule conjugate of step 2.

5 14. The method of claim 13, wherein the coupling agent of step 1 is selected from the group comprising bis(2-oxo-3-oxazolydiny)phosphonic chloride (BOP-Cl), bromo-tris-pyrrolidino-phosphonium hexafluorophosphate (PyBroP), benzotriazole-1-yl-oxy-tris-pyrrolidino-
10 phosphonium hexafluorophosphate (PyBOP), 2-(1H-benzotriazole-1-yl)-1,1,3,3-tetramethyluronium hexafluorophosphate (HBTU), dicyclohexyl carbodiimide, disuccinimidyl carbonate, 1-(3-dimethylaminopropyl)-3-ethylcarbodiimide (EDC), bis(2-oxo-3-oxazolydiny)phosphin, diisopropyl carbodiimide (DIPC),
15 2-(1H-benzotrioxazolyl)-1,1,3,3-tetramethyl-uronium tetrafluoroborate (TBTU), 2-(5-norbornen-2,3-dicarboxyimido)-1,1,3,3-tetramethyluronium tetrafluoroborate (TNTU), para-nitrophenylchloroformate, and
20 O-(N-succinimidy)-1,1,3,3-tetramethyluronium tetrafluoroborate (TSTU).

15. The method of claim 13, wherein the base of step 1 is selected from the group comprising triethylamine, N-methylmorpholine, pyridine, 1,8-diazabicyclo[5,4,0]-undec-7-ene, N,N-dimethyl aminopyridine, and N,N-diisopropyl ethylamine.

16. The method of claim 13, wherein the additives
of step 1 is selected from the group comprising
hydroxybenzotriazole, pentafluorophenol and *N*-hydroxy-
5 5-norboren-endo-2,3-dicarboximide.

FIG. 1




FIG. 2




FIG. 3




FIG. 4a




FIG. 4b




FIG. 5a




FIG. 5b




FIG. 6




FIG. 7




FIG. 8a




FIG. 8b




FIG. 9




FIG. 10a




FIG. 10b




FIG. 10c




FIG. 11




FIG. 12




FIG. 13





FIG. 14



INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR 99/00243

A. CLASSIFICATION OF SUBJECT MATTER		
IPC ⁶ : A 61 K 9/16; A 61 K 9/22; A 61 K 9/50; A 61 K 9/51; A 61 K 9/52		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC ⁶ : A 61 K; C 08 G		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
EPODOC, WPI		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 96/20 698 A2 (THE BOARD OF REGENTS acting for and on behalf of THE UNIVERSITY OF MICHIGAN), 11 July 1996 (11.07.96), claims.	1,2,4,5,8-12,13,15
A Y	WO 95/28 149 A1 (PIERRE FABRE MEDICAMENT), 26 October 1995 (26.10.95), claims.	1 2,3,5-7,10-12
A Y	EP 0 765 659 A1 (SHISEIDO COMPANY LIMITED), 02 April 1997 (02.04.97), column 1, lines 7-8; column 3, lines 51-59; column 4, lines 1-39; column 5, lines 19-42.	1 2,3,5-7,10-12
A	ROY P.D., New Derivatives of p-Hydroxyphenylmalonic acid, Research Disclosure, May 1981, No.205, Art.No.20509, page 175,176; page 176, column 1.	13-16
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.		
* Special categories of cited documents: „A“ document defining the general state of the art which is not considered to be of particular relevance „E“ earlier application or patent but published on or after the international filing date „L“ document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) „O“ document referring to an oral disclosure, use, exhibition or other means „P“ document published prior to the international filing date but later than the priority date claimed „T“ later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention „X“ document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone „Y“ document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art „&“ document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
29 July 1999 (29.07.99)		01 September 1999 (01.09.99)
Name and mailing address of the ISA/AT Austrian Patent Office Kohlmarkt 8-10; A-1014 Vienna Facsimile No. 1/53424/200		Authorized officer Krenn Telephone No. 1/53424/435

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR 99/00243

Im Recherchenbericht angeführtes Patentedokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
WD A2 9620698	11-07-1996	AU A1 47556/96 CA AA 2207961 EP A1 805678 JP T2 10511957 WD A3 9620698	24-07-1996 11-07-1996 12-11-1997 17-11-1998 22-01-1998
WD A1 9528149	26-10-1995	AT E 172639 AU A1 23478/95 AU B2 698796 CA AA 2187898 DE C0 69505697 DE T2 69505697 EP A1 804173 EP B1 804173 FR A1 2718642 FR B1 2718642 JP T2 9512002 NZ A 284826 US A 5733567	15-11-1998 10-11-1995 05-11-1998 26-10-1995 03-12-1998 10-06-1999 05-11-1997 28-10-1998 20-10-1995 12-07-1996 02-12-1997 19-12-1997 31-03-1998
EP A1 765659	02-04-1997	JP A2 9077657	25-03-1997